Data sheet



RT100




RUBITHERM[®] RT is a pure PCM, this heat storage material utilising the processes of phase change between solid and liquid (melting and congealing) to store and release large quantities of thermal energy at nearly constant temperature. The RUBITHERM[®] phase change materials (PCM's) provide a very effective means for storing heat and cold, even when limited volumes and low differences in operating temperature are applicable.

Properties for RT-line:

- high thermal energy storage capacity
- heat storage and release take place at relatively constant temperatures
- no supercooling effect, chemically inert
- long life product, with stable performance through the phase change cycles
- melting temperature range between -9 °C and 100 °C available

The most important data:	Typical Values	
Melting area	90-112	[°C]
Congealing area	main peak: 1 108-86 main peak: 1	[°C] 102
Heat storage capacity ± 7,5%	124	[kJ/kg]*
Combination of latent and sensible heat in a temperatur range of 90°C to 105C.	34	[Wh/kg]*
Specific heat capacity	2	[kJ/kg [.] K]
Density solid at 15°C	0,88	[kg/l]
Density liquid	0,77	[kg/l]
Heat conductivity (both phases)	0,2	[W/(m [.] K)]
Volume expansion	12,5	[%]
Flash point	312	[°C]
Max. operation temperature	120	[°C]



Rubitherm Technologies GmbH Imhoffweg 6 D-12307 Berlin phone: +49 (30) 7109622-0 E-Mail: info@rubitherm.com Web: www.rubitherm.com

The product information given is a nonbinding planning aid, subject to technical changes without notice. Version: 09.10.2020