

RT18HC




RUBITHERM® RT is a pure PCM, this heat storage material utilising the processes of phase change between solid and liquid (melting and congealing) to store and release large quantities of thermal energy at nearly constant temperature. The RUBITHERM® phase change materials (PCM's) provide a very effective means for storing heat and cold, even when limited volumes and low differences in operating temperature are applicable.

Properties for RT-line:

- high thermal energy storage capacity
- heat storage and release take place at relatively constant temperatures
- no supercooling effect, chemically inert
- long life product, with stable performance through the phase change cycles
- melting temperature range between -9 °C and 100 °C available

The most important data:	Typical Value	S	
Melting area	17-19 main peak: 18	[°C]	
Congealing area	19-17 main peak: 17	[°C]	
Heat storage capacity ± 7,5%	260	[kJ/kg]*	
Combination of latent and sensible heat in a temperatur range of 11°C to 26°C.	72	[Wh/kg]*	
Specific heat capacity	2	[kJ/kg·K]	
Density solid	0,88	[kg/l]	GHS08
Density liquid	0,77	[kg/l]	
Heat conductivity (both phases)	0,2	[W/(m·K)]	
Volume expansion	12,5	[%]	
Flash point	135	[°C]	
Max. operation temperature	50	[°C]	



Rubitherm Technologies GmbH Imhoffweg 6 D-12307 Berlin

phone: +49 (30) 7109622-0

E-Mail: info@rubitherm.com Web: www.rubitherm.com

The product information given is a nonbinding planning aid, subject to technical changes without notice.

Version: 09.10.2020

^{*}Measured with 3-layer-calorimeter.