

RT60

RUBITHERM® RT is a pure PCM, this heat storage material utilising the processes of phase change between solid and liquid (melting and congealing) to store and release large quantities of thermal energy at nearly constant temperature. The RUBITHERM® phase change materials (PCM's) provide a very effective means for storing heat and cold, even when limited volumes and low differences in operating temperature are applicable.




Properties for RT-line:

- high thermal energy storage capacity
- heat storage and release take place at relatively constant temperatures
- no supercooling effect, chemically inert
- long life product, with stable performance through the phase change cycles
- melting temperature range between -9 °C and 100 °C available

The most important data:

	Typical Values
Melting area	55-61 [°C] main peak: 60
Congeeing area	61-55 [°C] main peak: 61
Heat storage capacity ± 7,5% Combination of latent and sensible heat in a temperatur range of 53°C to 68 °C.	160 [kJ/kg]*
Specific heat capacity	40 [Wh/kg]*
Density solid at 15°C	2 [kJ/kg·K]
Density liquid at 80°C	0,88 [kg/l]
Heat conductivity (both phases)	0,77 [kg/l]
Volume expansion	0,2 [W/(m·K)]
Flash point	12,5 [%]
Max. operation temperature	>200 [°C]
	80 [°C]

Beispiel / example: RT60 Teilenthalpie / Partial enthalpy distribution*



Rubitherm Technologies GmbH
 Imhoffweg 6
 D-12307 Berlin
 phone: +49 (30) 7109622-0
 E-Mail: info@rubitherm.com
 Web: www.rubitherm.com

The product information given is a non-binding planning aid, subject to technical changes without notice.
 Version: 09.10.2020

*Measured with 3-layer-calorimeter.