

RT90HC (in development)



RUBITHERM® RT is a pure PCM, this heat storage material utilising the processes of phase change between solid and liquid (melting and congealing) to store and release large quantities of thermal energy at nearly constant temperature. The RUBITHERM® phase change materials (PCM's) provide a very effective means for storing heat and cold, even when limited volumes and low differences in operating temperature are applicable.

We look forward to discussing your particular questions, needs and interests with you.


Properties for RT-line:

- high thermal energy storage capacity
- heat storage and release take place at relatively constant temperatures
- no supercooling effect, chemically inert
- long life product, with stable performance through the phase change cycles
- melting temperature range between -9 °C and 100 °C available

The most important data:

	Typical Values	
Melting area	91-92	[°C]
	main peak: 91	
Congealing area	91-90	[°C]
	main peak: 90	
Heat storage capacity ± 7,5%	170	[kJ/kg]*
Combination of latent and sensible heat in a temperatur range of 83°C to 98°C.	47	[Wh/kg]*
Specific heat capacity	2	[kJ/kg·K]
Density solid at 25 °C	0,95	[kg/l]
Density liquid at 90 °C	0,85	[kg/l]
Heat conductivity (both phases)		[W/(m·K)]
Volume expansion		[%]
Flash point		[°C]
Max. operation temperature	120	[°C]

Beispiel: RT90HC Teilenthalpie / Partial enthalpy distribution



Rubitherm Technologies GmbH
 Imhoffweg 6
 D-12307 Berlin
 Tel: +49 (30) 7109622-0
 Fax: +49 (30) 7109622-22
 E-Mail: info@rubitherm.com
 Internet: www.rubitherm.com

The product information given is a non-binding planning aid, subject to technical changes without notice. Version: 06.08.2018

*Measured with 3-layer-calorimeter.